

LOBADUR® WS 2K Ultra

2-Component, waterborne finish based on polyurethane-resins with extremely high final hardness, great elasticity and excellent resistance against chemical wear.

Article No.:	11035	2004/42/CE
Gloss Level:	Extra matte (ca. 10*)	EU limit value for this product
Package Size:	5 kg, incl. Hardener	(cat. A/j): 140g/l (2007/2010)
Giscode:	W 3/DD	This product contains max 124g/l VOC
Solids:	40 ± 1% after mixing	(ready to use in mixture with Hardener)
Viscosity DIN 4:	23 ± 1s after mixing	

Range of Use: PVC and linoleum floors with normal to extremely high wear.
Suitable for sportsfloors.
Requirements according to DIN 18032 are met.

Information on Use:

- Shake mass, add hardener, ratio 5 : 1, and mix it by shaking.
- Should you only use part of the mass, use the LOBATool mixing jug.
- Do not put material directly on the floor, use the LOBATool sealing bucket.
- After mixing usable for 2 hours.

Setup Recommendations:

1. Prepare floor with a basic cleaning (care product remains must be completely cleaned off; otherwise trouble with adhesion)
2. Clean with clear water (neutralize)
3. Drying
4. Roll one coat of LOBADUR® WS 2K Ultra onto surface

Basic Cleaning:	PVC	Linoleum
	Basic cleaning with LOBACARE® Grundreiniger Spezial or LOBA® CareRemover Drying time ca. 2 hours	Basic cleaning with LOBA® CareRemover Drying over night

Covering Tool: LOBATool roller „Microfaser 60 – 80“

Covering Quantity: Roller application 60 - 80 g/m² (12 - 16 m²/kg), 6 – 8 g / square foot

Drying Time: Can be carefully walked on after 6 – 8 hours, light wear after 24 hours, final hardness reached after ca. 8 days

Thinner: The finish is ready-to-use and cannot be diluted! In case of unfavourable conditions the risk of drying can be delayed by adding LOBADUR® WS Argo. Add LOBADUR WS Argo only after mixing with hardener.

Storage and Transportation: Finish and hardener are not sensitive to frost; storable for 12 months; not a hazardous material according to ADR; hardener contains isocyanat; Xi irritant

The general information on the Use of LOBADUR® WS Products are part of this Information and must be noticed.

LOBA GmbH & Co. KG
Tel: +49 (0) 7156 357 169
Fax: + 49 (0) 7156 357 211
Mail: service@loba.de

* The gloss level is measured at 60°.
It depends on the thickness and the climatic conditions (temp, rel. Air humidity) during drying. The date is not binding.